

QUICKTEST 38®

Quicktest 38[®] serves to check if the treatment of polyolefins (polypropylene, polyethylene, polybutylene) has shown an effect onto the material. A stroke of the pen leaves a full line on the material if the material's surface tension has a value of 38 mN/m or more. If the material's surface tension is below 38 mN/m, the fluid contained in the pen will form small drops on the surface. The fluid applied to the surface will dry within seconds, it does not need to be wiped off anymore.

QUICKTEST 38° JUMBO

- better color presentation
- big line 15 mm
- optimal for testing large film areas





ADVANTAGES:

- extremely easy to handle
- perfect for quick checks on polyolefins
- no wiping off necessary
- lasting display of result
- archiving of the image possible

ATTENTION:

The test fluid of **Quicktest 38**° contains solvent. This might cause wrong results being displayed on materials not being solvent resistant, as PS for example.

Managing Director: Fritz P. Bloss Amtsgericht Mannheim HRB 511684 IdNr. DE813775094 **arcotest GmbH** Rotweg 25 D-71297 Moensheim Germany www.arcotest.info E-mail: info@arcotest.info Phone.: +49(0)7044 - 90 22 70 Fax: +49(0)7044 - 90 22 69